



# CITADEL® CONCRETE DENSIFIER

## DESCRIPTION AND USES

Citadel® Concrete Densifier is a liquid concrete-floor hardener. Concrete Densifier is a solution of sodium silicates designed to react with the concrete to seal the pores and chemically harden the surface.

## PRODUCT FEATURES AND BENEFITS

- Increases abrasion resistance
- Leaves no film that will wear off
- May be applied over stained/dyed concrete
- Improves chemical resistance
- Eliminates dusting
- Increases surface strength
- Resists oil and water penetration
- Treated surface is not slippery

## PRODUCTS

DESCRIPTION	SKU
Concrete Densifier 1 Gallon	353622
Concrete Densifier 5 Gallon Pail	353632

## COMPANION PRODUCTS

DESCRIPTION	SKU
Concrete Grout Coat 1 Gallon	353638
Concrete Grout Coat 5 Gallon Pail	353639
Concrete Polish Stain Guard 1 Gallon	353623
Concrete Polish Stain Guard 5 Gallon Pail	353633

## PRODUCT APPLICATION

### READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

#### CONCRETE REPAIR

All spalls and cracks must be chased out and repaired to ICRI standards using an appropriate patching material. If patching is required, use Citadel Concrete Repair Compound.

## PRODUCT APPLICATION (cont.)

### SURFACE PREPARATION (cont.)

**NEW CONCRETE:** New concrete should be allowed to cure for a minimum of 7 days. The concrete must be structurally sound, dry, and free of grease, oils, dust, curing compounds and other coatings or contaminants. Surface laitance must be removed. Concrete may be damp, but not puddled.

**PREVIOUSLY COATED:** Existing coatings must be removed. The preferred method of surface preparation is to mechanically abrade the floor by diamond grinding. The concrete must be structurally sound, dry, and free of grease, oils, dust, curing compounds and other coatings or contaminants. Surface laitance must be removed. Concrete may be damp, but not puddled.

### MIXING EQUIPMENT

Low speed drill and spiral mixing wand.

**Important:** Hand mixing will produce inconsistent results and is not an approved method.

### APPLICATION

Apply only when air, material and floor temperatures are above 35°F and rising at the time of application and relative humidity below 85%. Concrete Densifier is ready to use from the container. Apply a single coat of Concrete Densifier using a low pressure sprayer, roller, scrub pad or auto scrubber. A mechanical scrubber will increase the penetration and effectiveness of the product. Apply so that coverage results in a uniform wet surface without puddles. Concrete Densifier should soak into the concrete, and any excess material should be removed with a squeegee and not allowed to dry on the surface. Dried product will need to be removed with a grinder.

### THINNING

None required

### CLEAN-UP

Clean Tools and application equipment immediately after use with soap and water. Clean spills or drips while still wet with soap and water. Dried product will require mechanical abrasion for removal.



**CITADEL®  
CONCRETE DENSIFIER**

**PHYSICAL PROPERTIES**

		CONCRETE DENSIFIER
<b>Resin Type</b>		Sodium Silicate
<b>Solids By Volume</b>		20-25%
<b>Volatile Organic Compounds</b>		<=5 g/l
<b>Practical Coverage Rate</b>		200-300 sq.ft./gal. Coverage rate can vary depending on the texture and porosity of the concrete
<b>Dry Times at 77°F (25°C) and 50% Relative Humidity</b>	<b>Tack Free</b>	2-4 hours
	<b>Foot Traffic</b>	4 to 6 hours
<b>Shelf Life</b>		2 years
<b>Flash Point</b>		>200°F (93°C)
<b>CAUTION!</b>		Protect from freezing
<b>Safety Information</b>		See SDS

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.