



CITADEL® UL 80

DESCRIPTION AND USES

Citadel® UL 80 is a two component polyaspartic floor coating that provides low odor, excellent UV, chemical, and abrasion resistance plus a 24 hour return to service time. UL 80 is a versatile coating primarily used as top coat over broadcast systems. Smooth or solid color floors may leave an orange peel finish. UL 80 is sold clear, but may be pigmented using Rust-Oleum® Universal Tint Packs.

PRODUCT FEATURES AND BENEFITS

- Fast return to service time, Low Odor and can accept vehicle traffic in 24 hours
- UV Stable, excellent chemical, abrasion, and heat resistance
- Can be applied at temperatures between 30°F to 90°F
- Available in gloss finish

PRODUCT

SKU	DESCRIPTION (Clear)
390092	4 Gallon Kit
390096	10 Gallon Kit

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

The concrete surface must be free of all dirt, grease, oil, fats, and other contamination. Remove surface contamination by cleaning with Krud Kutter® PRO Cleaner Degreaser, detergent, or other suitable cleaner. Rinse thoroughly with clean, fresh water and allowed to dry.

NEW CONCRETE: New concrete should be allowed to cure for a minimum of 28 days. The concrete must be structurally sound, dry, and free of grease, oils, dust, curing compounds and other coatings or contaminants. Surface laitance must be removed. Concrete must be tested for relative humidity and or rising moisture vapor emission. Rates must not exceed 3 lb. per 1,000 sq. ft. over a 24 hour period as measured by calcium chloride test method ASTM F-1869 or RH in slab must not exceed 75% as tested per ASTM F2170. The preferred method of surface preparation is to mechanically abrade the floor by diamond grinding to achieve a final 80–120 grit finish, reference profile CSP-2 according to ICRI.

PREVIOUSLY COATED CONCRETE: Previously coated concrete must be in good sound condition with the existing coating tightly adhering to the concrete. In addition to the aforementioned cleaning the existing coating must be abraded to dull the finish and produce a slight surface profile. Remove all sanding dust by vacuum.

PRODUCT APPLICATION (cont.)

MIXING

Both components should be preconditioned to a minimum of 50° F (10°C) prior to use. Thoroughly mix each component separately before combining. If only using part of a container, be sure to use a separate mixer blade for each component to avoid cross contamination.

Pour the Part A and Part B components together in a clean, dry five-gallon container and power mix for a minimum of two minutes. Do not entrain air into the mixing. Do not mix more material than can be applied in 20-25 minutes.

If using less than a full container, combine the components using a mixing ratio of 1:1 by volume, Part A (Base) to Part B (Activator).

TINTING (Clear)

Pre-mix Universal Tint Packs prior to adding into floor coatings. Hand mixing until uniform in appearance is acceptable. Add Universal Tint Packs at 8 oz. per gallon of mixed floor coating material and combine thoroughly via power mix to achieve uniform colorant dispersal. **NOTE:** Some colors, including safety colors, may require additional coats if desired coverage is not achieved in the first application. **NOT FOR USE IN WATER BASED COATINGS**

If there are any questions on the tint process of this product, please consult our technical service department.

EQUIPMENT RECOMMENDATIONS

ROLLER: Use a high quality ¾ inch lint-free roller with a phenolic core.

BRUSH: Use a disposable natural fiber chip brush, 2-4 inch wide for cut in work.

APPLICATION

Apply only when air, material and floor temperatures are between 30-90°F (-1-32°C). Do not apply in direct sunlight or when temperature is rising. Colder environmental conditions can slow the cure of UL 80. For application outside of this temperature range, please contact Rust-Oleum Technical Service.

Immediately after mixing, pour the material onto the floor in a long, 8- to 12-inch-wide stripe.

NOTE: Do not scrape the sides or bottom of the container. Use only the material that flows naturally out of the container. Also, do not turn the container upside down and leave on the floor to drain. Doing so may result with unactivated material from the sidewall of the container being applied. This will cause soft spots in the coating.



CITADEL® UL 80

PRODUCT APPLICATION (cont.)

APPLICATION (cont.)

Use a rubber squeegee to spread the material out and achieve the 100-400 sq.ft./gal. spread rate. Back roll the material smooth using a 3/8" lint free roller with a phenolic core to smooth out the finish.

NOTE: Coverage rate can vary depending on the texture and porosity of the concrete.

THINNING: Not normally required.

CLEAN-UP: Acetone.

PERFORMANCE CHARACTERISTICS

TENSILE STRENGTH

METHOD: ASTM D412
TYPICAL VALUE: 6,000 psi

COMPRESSIVE STRENGTH

METHOD: ASTM C695
TYPICAL VALUE: 9,400 psi

ELONGATION

METHOD: ASTM D412
TYPICAL VALUE: 100

FILM HARDNESS, SHORE D

METHOD: ASTM D2240
TYPICAL VALUE: 78

GLOSS

METHOD: ASTM D523 @60°
TYPICAL VALUE: 90+

TABER ABRASION

METHOD: ASTM 4060, CS 17, 1,000-gram load
TYPICAL VALUE: Loss/1000 cycles = 28 mg

This coating complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

CHEMICAL RESISTANCE

CHEMICAL	RESULT
Acetic Acid 100%	C
Acetone	C
Ammonium Hydroxide 50%	RC
Benzene	C
Brine saturated H ₂ O	R
Chlorinated H ₂ O	R
Clorox H ₂ O	R
Diesel fuel	RC
Gasoline	RC
Gasoline/5% MTBE	RC
Gasoline/5% Methanol	RC
Hydrochloric Acid 20%	R
Hydrofluoric Acid 10%	NR
Hydraulic fluid (oil)	RC
Isopropyl Alcohol	R
Lactic Acid	RC
MEK	RC
Methanol	R
Methylene Chloride	C
Mineral Spirits	RC
Motor Oil	R
MTBE	C
Muriatic Acid 10%	R
NaCl/ H ₂ O 10%	R
Nitric Acid 20%	NR
Phosphoric Acid 10%	R
Phosphoric Acid 50%	NR
Potassium Hydroxide 10%	R
Potassium Hydroxide 20%	R, Dis
Propylene Carbonate	RC
Skydrol	C
Sodium Hydroxide 25%	R
Sodium Hydroxide 50%	R, Dis
Sodium Hypochlorite 10%	R
Sodium Bicarbonate	R
Stearic Acid	R
Sugar/ H ₂ O	R
Sulfuric Acid 10%	R
Sulfuric Acid >50%	RC
Toluene	R
1, 1,1-Trichlorethane	C
Trisodium Phosphate	R
Vinegar/ H ₂ O 5%	R
H ₂ O	R
H ₂ O 14 days at 82° C	RC
Xylene	RC

Chemical Resistance: Chart Key

R=recommended/little or no visible damage

RC=recommended conditional/some effect, swelling or discoloration

C=Conditional/Cracking-wash within one hour of spillage to avoid affects

NR=Not recommended

Dis=discolorative



CITADEL[®] UL 80

PHYSICAL PROPERTIES

		UL 80
Resin Type		Polyaspartic Polyurea
Weight	Per Gallon	9.0 lbs.
	Per Liter	1.1 kg/l
Solids by Volume		80%
Volatile Organic Compounds		<250 g/l**
Recommended Dry Film Thickness (DFT) Per Coat		6-12 mils
Wet Film Thickness (WFT) to Achieve DFT (unthinned material)		8-16 mils
Mixing Ratio		1:1 (Part A to Part B)
Induction Time		None required
Pot Life		30-35 minutes
Practical Coverage		100-200 sq.ft./gal. Coverage rate can vary depending on the texture and porosity of the concrete
Dry Times @ 72°F and 50% Relative Humidity†	Tack Free	2-4 hours
	Dry Hard	24 hours for vehicle traffic
	Recoat	2-12 hours*
Shelf Life		2 years
Safety Information		See SDS

Calculated values are shown and may vary slightly from the actual manufactured material.

† Extreme cold temperatures may slow cure times.

* If 12 hour recoat time has elapsed, the coating must be properly abraded and cleaned prior to recoating.

** Calculated Applied VOC

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.